



Application/Uses

- Hot Melt Adhesives
- Sealants

Product Description

Westlake ELEVATE[™] DR241AA is an ethylene vinyl acetate (EVA) copolymer with 24% VA content. It is a high viscosity EVA resin which is often used to improve low temperature performance. It contains a pellet handling additive commonly used in some EVA resins, particularly those having higher VA content and higher melt indexes. It is added to improve pellet flow.

Typical Physical Properties

<u>Property^a</u>	<u>Test Method^b</u>	<u>Typical Value, Units^c</u>
Melt Index	D 1238	3 g/10 min
Density	D 1505	949 kg/m ³ (0.949 g/cm ³)
DSC Peak Melting Temperature	D 3418	78°C (172°F)
Vicat Softening Point	D 1525	49°C (120°F)
Tensile Strength at Break	D 638	3,200 psi
Elongation at Break	D 638	1,000 %
Flexural Modulus – 1% Secant	D 790	4,500 psi
Hardness – Shore A	D 2240	87
Hardness – Shore D	D 2240	37

^a Unless noted otherwise, all tests are run at 23°C (73°F).

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

NOTES

Physical properties are measured on compression molded specimens.

FDA

Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Please contact Westlake Technical Services for recommended processing conditions.

NOTICE

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION
2801 Post Oak Blvd Suite 600 Houston, Texas
Customer Service: 1-800-545-9577