



# Westlake Polymers

Enhancing your life every day

# TYMAX™ GT4402

## Application/Uses

- Blown Film
- Packaging
- Tie-layer

## Product Description

Westlake GT4402 is an anhydride modified linear low density polyethylene designed for blown film extrusion that contains no slip and no antiblock additives. This resin is designed to function as a coextruded tie layer in multilayer film applications. Westlake GT4402 is designed to tie PE to resins that typically have poor bonding characteristics such as polyamide and EVOH.

## Typical Physical Properties

<u>Property<sup>a</sup></u>	<u>Test<sup>b</sup> Method</u>	<u>Typical Value, Units<sup>c</sup></u>
Melt Index (Condition 190°C/2.16 kg)	D1238	2.4 g/10 min
Density	D4883	919 kg/m <sup>3</sup> (0.919) g/cm <sup>3</sup>
Vicat Softening Point	D3418	97° C (207° F)
DSC Melting Point	D3418	122° C (252° F)

<sup>A</sup> Unless noted otherwise, all tests are run at 23 °C (73 °F) and 50% relative humidity.

<sup>B</sup> Unless noted otherwise, the test method is ASTM.

<sup>C</sup> Units are in SI or US customary units.

## FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

## PROCESSING

For assistance with applications and temperature profiles, contact the Westlake Technical Services Department at 903-242-7693.

## COMMENTS

The data listed above represents typical values as measured by Westlake. They are given for information only, and no guarantee of their accuracy is made. The product is sold upon condition that purchasers shall make their own tests to determine the characteristics of the product and the suitability of the product for their particular purpose.

*Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

**WESTLAKE CHEMICAL CORPORATION**  
2801 Post Oak Blvd Suite 600 Houston, Texas  
Customer Service: 1-800-545-9577